

Application No: 10/663,023      Docket No.: Q176-US1


Page 3

IN THE CLAIMSRECEIVED  
CENTRAL FAX CENTER  
OCT 11 2006

Please amend the claims as follows:

1. (original) An electrochemical device, comprising:  
a blended electrolyte including one or more polyalkylene glycol dialkyl ethers,  
one or more alkali metal salts, and one or more siloxane polymers.
2. (original) The device of claim 1, wherein the one or more polyalkylene glycol dialkyl ethers includes one or more polyethylene glycol dialkyl ethers.
3. (original) The device of claim 1, wherein the one or more siloxane polymers includes one or more poly(siloxane alkylene oxide)s.
4. (withdrawn) The device of claim 1, wherein the one or more siloxane polymers includes one or more poly(siloxane-g-ethylene oxide).
5. (original) The device of claim 1, wherein the siloxane polymer includes at least one material selected from the group consisting of those represented by the following Formulas I - VI:

Formula I:




where, R and R'' are alkyl groups and R' is hydrogen or an alkyl group; R''' is alkyl or hydrogen; Q is hydrogen or a cross-linker, p is 0 or greater than 0; n is from 1 to 100; x is from 1 to 30; and Z is an alkyl or aryl group;

Application No: 10/663,023 Docket No.: Q176-US1


Page 4

Formula II:




where, R and R'' are alkyl groups and R' is hydrogen or an alkyl group; R<sub>1</sub> is a spacer made up of one or more CH<sub>2</sub> groups; R''' is alkyl or hydrogen; Q is hydrogen or a cross-linker; p is 0 or greater than 0; n is from 1 to 100; x is 2 to 25; and Z is an alkyl or aryl group;

Formula III:



wherein R'' and R' are alkyl groups; R<sub>1</sub> and R<sub>2</sub> are hydrogen or alkyl group; R''' is alkyl or hydrogen; Q is hydrogen or a cross-linker; p is 0 or greater than 0; n is from 1 to 100; x is from 1 to 30; y is from 1 to 30; Z is alkyl or aryl group;

Formula IV:




wherein R is a spacer made up of one or more CH<sub>2</sub> groups; R' is a spacer made up of one or more CH<sub>2</sub> groups; R'' and R''' are alkyl group; R<sub>1</sub> and R<sub>2</sub> are hydrogen or alkyl group; R''' is alkyl or hydrogen; Q is hydrogen or a cross-linker; p is 0 or greater than 0; n is from 1 to 100; x is from 1 to 30; y is from 1 to 30; Z is alkyl or aryl group; and

Formula V:

Application No: 10/663,023


Docket No.: Q176-US1

Page 5



wherein R and R' are alkyl groups; R<sub>1</sub> is hydrogen or alkyl group; R''' is alkyl or hydrogen; Q is hydrogen or a cross-linker; p is 0 or greater than 0; n is from 1 to 100; x is from 1 to 30; R' is an alkyl or aryl group; and

Formula VI:



wherein R and R' are alkyl groups; R<sub>1</sub> is hydrogen or an alkyl group; R<sub>2</sub> is a spacer made up of one or more CH<sub>2</sub> groups; R''' is alkyl or hydrogen; Q is hydrogen or a cross-linker; p is 0 or greater than 0; n is from 1 to 100; x is from 1 to 30; R' is an alkyl or aryl group.

6. (withdrawn) The device of claim 5, wherein the siloxane polymer includes at least two materials selected from the group consisting of those represented by Formulas I – VI.

7. (canceled)

8. (withdrawn) The device of claim 5, wherein the one or more polyalkylene glycol dialkyl ethers includes at least one material selected from the group consisting of those represented by Formula II.

9. (withdrawn) The device of claim 5, wherein the one or more polyalkylene glycol dialkyl ethers includes at least one material selected from the group consisting of those represented by Formula III.

Application No: 10/663,023      Docket No.: Q176-US1

Page 6

10. (withdrawn) The device of claim 5, wherein the one or more polyalkylene glycol dialkyl ethers includes at least one material selected from the group consisting of those represented by Formula IV.


11. (withdrawn) The device of claim 5, wherein the one or more polyalkylene glycol dialkyl ethers includes at least one material selected from the group consisting of those represented by Formula V.

12. (withdrawn) The device of claim 5, wherein the one or more polyalkylene glycol dialkyl ethers includes at least one material selected from the group consisting of those represented by Formula VI.

13. (withdrawn) The device of claim 5, wherein Z is methyl, ethyl, propyl or phenyl group.

14. (original) The device of claim 5, wherein the one or more polyalkylene glycol dialkyl ethers includes at least one material selected from the group consisting of those represented by the following Formula IX:

Formula IX:



wherein n = 3 to 8.

15. (original) The device of claim 1, wherein the molecular weight of polyalkylene glycol dialkyl ether is less than 1,000 g/mol.

16. (original) The device of claim 1, wherein the content of polyalkylene glycol dialkyl ether is in a range of 0.5 to 99.5 % of the total weight of polymer in the electrolyte.

17. (original) The device of claim 1, wherein the content of polyalkylene glycol dialkyl ether is in a range of 20 % to 60 % of the total weight of polymer in the electrolyte.

Application No: 10/663,023      Docket No.: Q176-US1

Page 7

18. (original) The device of claim 1, wherein the one or more alkali metal salts includes a lithium salt.

19. (original) The device of claim 18, wherein a ratio of [EO]/[Li] in the electrolyte is in a range of 5 to 50.

20. (original) The device of claim 1, wherein the one or more alkali metal salts includes one or more components selected from the group consisting of LiClO<sub>4</sub>, LiBF<sub>4</sub>, LiAsF<sub>6</sub>, LiPF<sub>6</sub>, LiCF<sub>3</sub>SO<sub>3</sub>, Li(CF<sub>3</sub>SO<sub>2</sub>)<sub>2</sub>N, Li(CF<sub>3</sub>SO<sub>2</sub>)<sub>3</sub>C, LiN(SO<sub>2</sub>C<sub>2</sub>F<sub>5</sub>)<sub>2</sub>, lithium alkyl fluorophosphates, and lithium bis(chelato)borates.

21. (original) The device of claim 1, wherein at least one of the one or more siloxane polymers is cross-linked.

22. (original) The device of claim 1, wherein the one or more siloxane polymers includes at least two siloxane polymers and at least one of the siloxane polymers is cross-linked.

23. (original) The device of claim 1, wherein at least one of the one or more siloxane polymers is cross-linked with a cross-linker that includes a moiety selected from a group consisting of moieties having the formula O-(CH<sub>2</sub>CH<sub>2</sub>O)<sub>q</sub> and Si-O-(Si-O)<sub>k</sub>-Si where q is in a range of 4 to 30 and k is in a range of 5 to 30.

24. (original) The device of claim 1, wherein at least one of the one or more siloxane polymers and the one or more polyalkylene glycol dialkyl ethers serves a member of an interpenetrating network.

25. (original) The device of claim 1, wherein the electrolyte includes one or more network polymers forming an interpenetrating network with at least one other polymer

Application No: 10/663,023      Docket No.: Q176-US1

Page 8

selected from the group consisting of the one or more siloxane polymers and the one or more polyalkylene glycol dialkyl ethers.

26. (original) The device of claim 25, wherein at least one of the one or more network polymers is selected from a group consisting of a polyacrylate and a polymethacrylate.

27. (original) The device of claim 26, wherein at least one of the one or more network polymers is cross-linked.

28. (original) The device of claim 25, wherein at least one of the one or more network polymers is selected from the group consisting of polyacrylates and polymethacrylates.

29. (original) The device of claim 25, wherein at least one of the one or more network polymers is selected so as to be fabricated from a monomer having four or more functionalities.

30. (original) The device of claim 1, further comprising:  
one or more matrix polymers.

31. (original) The device of claim 30, wherein the one or more matrix polymers includes at least one component selected from the group consisting of: polyacrylonitrile, poly(vinylidene fluoride), poly(vinylidene fluoride-co-hexafluoropropylene), polystyrene, polyvinyl chloride, poly(alkyl methacrylate), poly(alkyl acrylate), styrene butadiene rubber (SBR), and poly(vinyl acetate).

32. (original) The device of claim 1, wherein the electrolyte is a solid.

33. (previously presented) The device of claim 1, further comprising:  
at least one lithium metal oxide cathode;  
at least one porous separator; and  
at least one anode including at least one material selected from the group

Application No: 10/663,023      Docket No.: Q176-US1

Page 9

consisting of: graphite,  $\text{Li}_4\text{Ti}_5\text{O}_{12}$ , tin alloys, silica alloys, intermetallic compounds, and lithium metal.

34. (original) The electrochemical device of claim 33, wherein the lithium metal oxide cathode includes at least one material selected from the group consisting of  $\text{Li}_x\text{VO}_y$ ,  $\text{LiCoO}_2$ ,  $\text{LiNiO}_2$ ,  $\text{LiMn}_{0.5}\text{Ni}_{0.5}\text{O}_2$ ,  $\text{LiMn}_{0.3}\text{Co}_{0.3}\text{Ni}_{0.3}\text{O}_2$ ,  $\text{LiFePO}_4$ ,  $\text{LiMn}_2\text{O}_4$ ,  $\text{LiFeO}_2$ , vanadium oxide,  $\text{LiNi}_{1-x}\text{Co}_y\text{Me}_z\text{O}_2$  wherein Me is Al, Mg, Ti, B, Ga, Si, Mn, Zn, and  $\text{LiMc}_{0.5}\text{Mn}_{1.5}\text{O}_4$  wherein Mc is divalent metal such as Ni, Co, Fe, Cr, and Cu.

35.-62 (canceled)

63. (new) The device of claim 5, wherein the one or more polyalkylene glycol dialkyl ethers includes at least one material selected from the group consisting of those represented by Formula I.

64. (new) The device of claim 7, wherein at least one of the materials represented by Formula I is represented by Formula I with  $p = 0$ .